

GEON[®] Rigid M3005

GEON Performance Solutions - Rigid Polyvinyl Chloride

Thursday, November 2, 2023

	General Information						
General							
Material Status	Commercial: Active						
Availability	 Africa & Middle East Asia Pacific Latin America		North America				
Features	Low Smoke Emission						
Agency Ratings	NSF STD-14	NSF Type I					
Forms	Pellets						

	ASTM & I	SO Propertie	es ¹		
Physical	Nominal Value	(English)	Nominal Value	(SI)	Test Method
Density / Specific Gravity	1.40		1.40		ASTM D792
Spiral Flow	24.0	in	61.0	cm	
Molding Shrinkage - Flow	2.0E-3 to 5.0E-3	in/in	0.20 to 0.50	%	ASTM D955
PVC Cell Classification	11432		11432		ASTM D1784
Mechanical	Nominal Value	(English)	Nominal Value	(SI)	Test Method
Tensile Modulus ²	450000	psi	3100	MPa	ASTM D638
Tensile Strength ² (Yield)	7400	psi	51.0	MPa	ASTM D638
Flexural Modulus	450000	psi	3100	MPa	ASTM D790
Flexural Strength	13300	psi	91.7	MPa	ASTM D790
Impact	Nominal Value	(English)	Nominal Value	(SI)	Test Method
Notched Izod Impact - Across Flow					ASTM D256A
73°F (23°C), 0.125 in (3.18 mm), Compression Molded	1.0	ft∙lb/in	53	J/m	
73°F (23°C), 0.250 in (6.35 mm), Compression Molded	0.70	ft∙lb/in	37	J/m	
Hardness	Nominal Value	(English)	Nominal Value	(SI)	Test Method
Durometer Hardness (Shore D, 10 sec)	82		82		ASTM D2240
Thermal	Nominal Value	(English)	Nominal Value	(SI)	Test Method
Deflection Temperature Under Load					ASTM D648
66 psi (0.45 MPa), Unannealed, 0.250 in (6.35 mm)	163	°F	72.8	°C	
264 psi (1.8 MPa), Unannealed, 0.250 in (6.35 mm)	162	°F	72.2	°C	
Flammability	Nominal Value	(English)	Nominal Value	(SI)	Test Method
Flame Rating (0.06 in (1.5 mm), ALL)	V-0		V-0		UL 94
	Processi	ng Informati	on		
Injection	Nominal Value	(English)	Nominal Value	(SI)	

Processing (Melt) Temp

Notes

¹ Typical properties: these are not to be construed as specifications.

² Type I, 2.0 in/min (51 mm/min)

IMPORTANT: The information contained herein is believed to be accurate, but this information should not be construed as a product specification. It is offered for your consideration, investigation, testing, and verification. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end-product performance. Due to variations in methods, conditions, and equipment used commercially to process this product, no warranties or guarantees are made as to the suitability of this product for any particular application. Full-scale testing and end product performance are the responsibility of the user. GEON Performance Solutions is not liable for and the user assumes all risk and liability of any use or handling of this product. GEON PERFORMANCE SOLUTIONS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.

193 to 202 °C

380 to 395 °F