

GEON® Rigid M3850

GEON Performance Solutions - Rigid Polyvinyl Chloride

Thursday, November 2, 2023

General Information

General			
Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• Impact Modifier		
Features	• General Purpose	• High Flow	• Impact Modified
Uses	• Appliances • Business Equipment	• Construction Applications • Electrical/Electronic Applications	• General Purpose • Telecommunications
Forms	• Pellets		

ASTM & ISO Properties ¹

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.33	1.33	ASTM D792
Spiral Flow	44.0 in	112 cm	
Molding Shrinkage - Flow	2.0E-3 to 5.0E-3 in/in	0.20 to 0.50 %	ASTM D955
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus ²	330000 psi	2280 MPa	ASTM D638
Tensile Strength ² (Yield)	6300 psi	43.4 MPa	ASTM D638
Tensile Elongation ² (Break)	35 %	35 %	ASTM D638
Flexural Modulus	340000 psi	2340 MPa	ASTM D790
Flexural Strength	9700 psi	66.9 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256A
0°F (-18°C), 0.125 in (3.18 mm), Injection Molded	2.0 ft·lb/in	110 J/m	
32°F (0°C), 0.125 in (3.18 mm), Injection Molded	5.0 ft·lb/in	270 J/m	
73°F (23°C), 0.125 in (3.18 mm), Injection Molded	12 ft·lb/in	640 J/m	
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore D)	79	79	ASTM D2240
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed, 0.250 in (6.35 mm)	162 °F	72.2 °C	
66 psi (0.45 MPa), Annealed, 0.250 in (6.35 mm)	167 °F	75.0 °C	
264 psi (1.8 MPa), Unannealed, 0.250 in (6.35 mm)	156 °F	68.9 °C	
264 psi (1.8 MPa), Annealed, 0.250 in (6.35 mm)	163 °F	72.8 °C	
RTI Elec	122 °F	50.0 °C	UL 746B
RTI Imp	122 °F	50.0 °C	UL 746B
RTI Str	122 °F	50.0 °C	UL 746B

IMPORTANT: The information contained herein is believed to be accurate, but this information should not be construed as a product specification. It is offered for your consideration, investigation, testing, and verification. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end-product performance. Due to variations in methods, conditions, and equipment used commercially to process this product, no warranties or guarantees are made as to the suitability of this product for any particular application. Full-scale testing and end product performance are the responsibility of the user. GEON Performance Solutions is not liable for and the user assumes all risk and liability of any use or handling of this product. GEON PERFORMANCE SOLUTIONS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.

GEON® Rigid M3850

GEON Performance Solutions - Rigid Polyvinyl Chloride

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating	<ul style="list-style-type: none"> • V-0 • 5VA 	<ul style="list-style-type: none"> • V-0 • 5VA 	UL 94

Additional Information	Nominal Value (English)	Nominal Value (SI)
CSA Flammability ³ (63.0 mil (1.60 mm))	<ul style="list-style-type: none"> • V-0 • 5VA 	<ul style="list-style-type: none"> • V-0 • 5VA

Processing Information

Injection	Nominal Value (English)	Nominal Value (SI)
Processing (Melt) Temp	390 to 410 °F	199 to 210 °C

Notes

¹ Typical properties: these are not to be construed as specifications.

² Type I, 2.0 in/min (51 mm/min)

³ All Colors

IMPORTANT: The information contained herein is believed to be accurate, but this information should not be construed as a product specification. It is offered for your consideration, investigation, testing, and verification. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end-product performance. Due to variations in methods, conditions, and equipment used commercially to process this product, no warranties or guarantees are made as to the suitability of this product for any particular application. Full-scale testing and end product performance are the responsibility of the user. GEON Performance Solutions is not liable for and the user assumes all risk and liability of any use or handling of this product. GEON PERFORMANCE SOLUTIONS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.