

# GEON® Rigid M4600

## GEON Performance Solutions - Rigid Polyvinyl Chloride

Thursday, November 2, 2023

| General Information |   |  |               |  |  |  |
|---------------------|---|--|---------------|--|--|--|
| General             |   |  |               |  |  |  |
| Material Status     | Commercial: Active  |  |               |  |  |  |
| Availability        | <ul><li>Africa &amp; Middle East</li><li>Asia Pacific</li></ul> | <ul><li>Europe</li><li>Latin America</li></ul> | North America |  |  |  |
| Additive            | Impact Modifier   |  |               |  |  |  |
| Features            | High Flow   | <ul> <li>Impact Modified</li> </ul>            |               |  |  |  |
| Uses                | Battery Cases   |  |               |  |  |  |
| Appearance          | <ul> <li>Clear/Transparent</li> </ul>                           |  |               |  |  |  |
| Forms               | Pellets   |  |               |  |  |  |

|   | ASTM & I         | SO Propertie | es <sup>1</sup> |      |             |
|---|------------------|--------------|-----------------|------|-------------|
| Physical  | Nominal Value    | (English)    | Nominal Value   | (SI) | Test Method |
| Density / Specific Gravity                        | 1.36             |              | 1.36            |      | ASTM D792   |
| Spiral Flow                                       | 40.0             | in           | 102             | cm   |             |
| Molding Shrinkage - Flow                          | 2.0E-3 to 5.0E-3 | in/in        | 0.20 to 0.50    | %    | ASTM D955   |
| Mechanical  | Nominal Value    | (English)    | Nominal Value   | (SI) | Test Method |
| Tensile Modulus <sup>2</sup>                      | 460000           | psi          | 3170            | MPa  | ASTM D638   |
| Tensile Strength <sup>2</sup> (Yield)             | 8000             | psi          | 55.2            | MPa  | ASTM D638   |
| Tensile Elongation <sup>2</sup> (Break)           | 30               | %            | 30              | %    | ASTM D638   |
| Flexural Modulus                                  | 440000           | psi          | 3030            | MPa  | ASTM D790   |
| Flexural Strength                                 | 13000            | psi          | 89.6            | MPa  | ASTM D790   |
| Impact  | Nominal Value    | (English)    | Nominal Value   | (SI) | Test Method |
| Notched Izod Impact                               |                  |              |                 |      | ASTM D256A  |
| 73°F (23°C), 0.125 in (3.18 mm), Injection Molded | 0.80             | ft·lb/in     | 43              | J/m  |             |
| Hardness  | Nominal Value    | (English)    | Nominal Value   | (SI) | Test Method |
| Durometer Hardness (Shore D)                      | 81               |              | 81              |      | ASTM D2240  |
| Thermal   | Nominal Value    | (English)    | Nominal Value   | (SI) | Test Method |
| Deflection Temperature Under Load                 |                  |              |                 |      | ASTM D648   |
| 66 psi (0.45 MPa), Unannealed, 0.250 in (6.35 mm) | 151              | °F           | 66.1            | °C   |             |
| 66 psi (0.45 MPa), Annealed, 0.250 in (6.35 mm)   | 158              | °F           | 70.0            | °C   |             |
| 264 psi (1.8 MPa), Unannealed, 0.250 in (6.35 mm) | 145              | °F           | 62.8            | °C   |             |
| 264 psi (1.8 MPa), Annealed, 0.250 in (6.35 mm)   | 154              | °F           | 67.8            | °C   |             |
| RTI Elec  | 122              | °F           | 50.0            | °C   | UL 746B     |
| RTI Imp   | 122              | °F           | 50.0            | °C   | UL 746B     |
| RTI Str   | 122              | °F           | 50.0            | °C   | UL 746B     |
| Flammability                                      | Nominal Value    | (English)    | Nominal Value   | (SI) | Test Method |
| Flame Rating                                      |                  |              |                 |      | UL 94       |
| 0.06 in (1.5 mm), Transparents                    | V-0              |              | V-0             |      |             |

IMPORTANT: The information contained herein is believed to be accurate, but this information should not be construed as a product specification. It is offered for your consideration, investigation, testing, and verification. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end-product performance. Due to variations in methods, conditions, and equipment used commercially to process this product, no warranties or guarantees are made as to the suitability of this product for any particular application. Full-scale testing and end product performance are the responsibility of the user. GEON Performance Solutions is not liable for and the user assumes all risk and liability of any use or handling of this product. GEON PERFORMANCE SOLUTIONS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.

### **GEON® Rigid M4600**

# GEON Performance Solutions - Rigid Polyvinyl Chloride

| Optical                                   | Nominal Value | (English) | Nominal Value | (SI) | Test Method |
|---|---------------|-----------|---------------|------|-------------|
| Light Transmittance (125.0 mil (3175 μm)) | 82.0          | %         | 82.0          | %    | ASTM D1003  |
| Haze (125.0 mil (3175 μm))                | 4.00          | %         | 4.00          | %    | ASTM D1003  |

| Processing Information |               |           |               |      |  |
|------------------------|---------------|-----------|---------------|------|--|
| Injection              | Nominal Value | (English) | Nominal Value | (SI) |  |
| Processing (Melt) Temp | 390 to 400    | °F        | 199 to 204    | °C   |  |

#### **Notes**

<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>&</sup>lt;sup>2</sup> Type I, 2.0 in/min (51 mm/min)