

# Dynaflex™ G2701C

## Thermoplastic Elastomer

### Key Characteristics

#### Product Description

Dynaflex™ G2701C is an easy processing TPE designed for injection molding and extrusion applications that require FDA compliance.

- Adhesion to Polypropylene
- Excellent Colorability
- Rubbery Feel
- Soft Touch

#### General

Material Status	• Commercial: Active		
Regional Availability	• Asia Pacific		
Features	• Good Colorability	• Good Stability	• Recyclable Material
	• Good Processability		
Uses	• Consumer Applications	• Personal Care	
	• Overmolding	• Transparent or Translucent Parts	
Agency Ratings	• FDA 21 CFR 177.2600 <sup>1</sup>		
RoHS Compliance	• RoHS Compliant		
Appearance	• Clear/Transparent		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

### Technical Properties <sup>2</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	0.900	0.900	ASTM D792
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress <sup>3, 4</sup> (300% Strain, 73°F (23°C))	645 psi	4.45 MPa	ASTM D412
Tensile Strength <sup>3, 4</sup> (Break, 73°F (23°C))	900 psi	6.21 MPa	ASTM D412
Tensile Elongation <sup>3, 4</sup> (Break, 73°F (23°C))	600 %	600 %	ASTM D412
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 10 sec)	65	65	ASTM D2240
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity			ASTM D3835
392°F (200°C), 1340 sec <sup>-1</sup>	42.8 Pa·s	42.8 Pa·s	
392°F (200°C), 11200 sec <sup>-1</sup>	10.5 Pa·s	10.5 Pa·s	

#### Additional Information

Dynaflex™ G2701C can be recycled as a filler or impact modifier for polyolefins, or can be recycled by grinding and reintroduction to the molding process. Similar to PP or PE recycling process, if separated appropriately, it can be recycled many times.

Municipality waste stream recycle code is "7" which is designated for "Other".

Please contact GLS Thermoplastic Elastomers for a copy of our Recyclability Compliance letter.

## Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Suggested Max Regrind	20 %	20 %
Rear Temperature	270 to 340 °F	132 to 171 °C
Middle Temperature	310 to 380 °F	154 to 193 °C
Front Temperature	335 to 405 °F	168 to 207 °C
Nozzle Temperature	335 to 405 °F	168 to 207 °C
Mold Temperature	60 to 80 °F	16 to 27 °C
Back Pressure	50.0 to 150 psi	0.345 to 1.03 MPa
Screw Speed	25 to 75 rpm	25 to 75 rpm

## Injection Notes

Color concentrates with polypropylene (PP), ethylene vinyl acetate (EVA), or low density polyethylene (LDPE) carriers are most suitable for coloring Dynaflex™ G2701C. Improved color dispersion can be achieved by using higher melt flow concentrates (with a melt flow from 25 - 40 g/10 min). Typical loadings for color concentrates are 1% to 5% by weight. Liquid color can be used, but mineral oil based carriers may have a significant effect on the final hardness value. Concentrates based on PVC should not be used. A high color match consistency can be obtained by using precolored compounds available from GLS. The final determination of color concentrate suitability should be determined by customer trials.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels up to 20% can be used with Dynaflex™ G2701C with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Dynaflex™ G2701C has excellent melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 8 - 10 minutes or longer.

Drying is not Required

Injection Speed: 1 to 5 in/sec  
 1st Stage - Boost Pressure: 350 to 650 psi  
 2nd Stage - Hold Pressure: 50% of Boost  
 Hold Time (Thick Part): 4 to 10 sec  
 Hold Time (Thin Part): 1 to 3 sec

## Notes

<sup>1</sup> Please contact GLS Thermoplastic Elastomers for a copy of the FDA compliance letter.

<sup>2</sup> Typical values are not to be construed as specifications.

<sup>3</sup> Die C

<sup>4</sup> 2 hr

## CONTACT INFORMATION

## North America

Avon Lake, United States  
 33587 Walker Road  
 Avon Lake, OH, United States ,  
 44012  
 +1 440 930 1000  
 +1 844 4AVIENT

## South America

Sao Paulo, Brazil  
 Av. Francisco Nakasato, 1700  
 13295-000 Itupeva  
 Sao Paulo, Brazil  
 +55 11 4593 9200

## Asia

Shanghai, China  
 2F, Block C  
 200 Jinsu Road  
 Pudong, 201206  
 Shanghai, China  
 +86 (0) 21 6028 4888

## Europe

Pommerloch, Luxembourg  
 19 Route de Bastogne  
 Pommerloch, Luxembourg , L-9638  
 +352 269 050 35



avient.com

Copyright ©, 2020 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.