

Dynaflex™ G7702-9001-02

Thermoplastic Elastomer

Key Characteristics

Product Description

Dynaflex™ G7702-9001-02 is a performance TPE designed for a wide variety of applications.

- Excellent Dimensional Stability
- Excellent Heat Stability
- High Resilience
- Low Compression Set
- Overmold Adhesion to Polypropylene

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Latin America • North America	
Features	• Good Dimensional Stability • Good Thermal Stability	• Low Compression Set • Resilient	
Uses	• Appliance Components • Automotive Applications	• Gaskets • Lawn and Garden Equipment	• Overmolding • Seals
RoHS Compliance	• RoHS Compliant		
Automotive Specifications	• FMVSS 302		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Technical Properties¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.10	1.10	ASTM D792
Molding Shrinkage - Flow	0.014 to 0.020 in/in	1.4 to 2.0 %	ASTM D955
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress ^{2,3} (100% Strain, 73°F (23°C))	140 psi	0.965 MPa	ASTM D412
Tensile Stress ^{2,3} (300% Strain, 73°F (23°C))	390 psi	2.69 MPa	ASTM D412
Tensile Strength ^{2,3} (Break, 73°F (23°C))	550 psi	3.79 MPa	ASTM D412
Tensile Elongation ^{2,3} (Break, 73°F (23°C))	480 %	480 %	ASTM D412
Tear Strength	120 lbf/in	21.0 kN/m	ASTM D624
Compression Set			ASTM D395B
73°F (23°C), 22 hr	11 %	11 %	
158°F (70°C), 22 hr	22 %	22 %	
212°F (100°C), 22 hr	28 %	28 %	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 10 sec)	37	37	ASTM D2240
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity			ASTM D3835
392°F (200°C), 11200 sec ⁻¹	10.2 Pa·s	10.2 Pa·s	

Copyright © 2020 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Suggested Max Regrind	20 %	20 %
Rear Temperature	340 to 380 °F	171 to 193 °C
Middle Temperature	380 to 470 °F	193 to 243 °C
Front Temperature	400 to 490 °F	204 to 254 °C
Nozzle Temperature	420 to 490 °F	216 to 254 °C
Mold Temperature	60 to 100 °F	16 to 38 °C
Back Pressure	0.00 to 120 psi	0.00 to 0.827 MPa
Screw Speed	25 to 100 rpm	25 to 100 rpm

Injection Notes

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels up to 20% can be used with Dynaflex™ G7702-9001-02 can with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Dynaflex™ G7702-9001-02 has excellent melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 8 - 10 minutes or longer.

Drying is not Required

Injection Speed: 1 to 3 in/sec

1st Stage - Boost Pressure: 250 to 1000 psi

2nd Stage - Hold Pressure: 30% of Boost

Hold Time (Thick Part): 3 to 10 sec

Hold Time (Thin Part): 1 to 3 sec

Notes

¹ Typical values are not to be construed as specifications.

² Die C

³ 2 hr

CONTACT INFORMATION

North America

Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States ,
44012
+1 440 930 1000
+1 844 4AVIENT

South America

Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia

Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe

Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35



avient.com

Copyright ©, 2020 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.