

# Versaflex™ HC MT226

## Thermoplastic Elastomer

### Key Characteristics

#### Product Description

Versaflex™ HC MT226 is an exceptionally clear, high performance TPE developed for medical tubing for healthcare. Versaflex™ HC MT226 has been specially formulated to be free of any plasticizers .  
New Product. Commercial specifications have not been established.

- Flexible
- Formulated without Plasticizers
- High Clarity

#### General

Material Status	• Commercial: Active	
Regional Availability	• Africa & Middle East • Asia Pacific	• Latin America • North America
Features	• Good Flexibility	• High Clarity
Uses	• Medical/Healthcare Applications	• Tubing
Agency Ratings	• FDA Unspecified Rating • ISO 10993 Part 4	• ISO 10993 Part 5 • USP Class VI <sup>1</sup>
RoHS Compliance	• RoHS Compliant	
Appearance	• Clear/Transparent	
Forms	• Pellets	
Processing Method	• Extrusion	

### Technical Properties <sup>2</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	0.890	0.890	ASTM D792
Films	Typical Value (English)	Typical Value (SI)	Test Method
Oxygen Permeability			ASTM D3985
70°F (21°C), 73 mil (1800 µm)	990 $\frac{\text{cm}^3 \cdot \text{mil}}{100 \text{ in}^2 \cdot \text{atm} / 24 \text{ hr}}$	390 $\frac{\text{cm}^3 \cdot \text{mm} / \text{m}^2 \cdot \text{at}}{\text{m} / 24 \text{ hr}}$	
Oxygen Transmission Rate			ASTM D3985
70°F (21°C), 73 mil (1800 µm)	13 $\frac{\text{cm}^3 / 100 \text{ in}^2 / 24 \text{ hr}}$	210 $\frac{\text{cm}^3 / \text{m}^2 / 24 \text{ hr}}$	
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress <sup>3, 4</sup> (300% Strain, 73°F (23°C))	885 psi	6.10 MPa	ASTM D412
Tensile Strength <sup>3, 4</sup> (Break, 73°F (23°C))	1600 psi	11.0 MPa	ASTM D412
Tensile Elongation <sup>3, 4</sup> (Break, 73°F (23°C))	600 %	600 %	ASTM D412
Compression Set			ASTM D395B
72°F (22°C), 22 hr	20 %	20 %	
113°F (45°C), 22 hr	51 %	51 %	
158°F (70°C), 22 hr	67 %	67 %	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 10 sec)	84	84	ASTM D2240

Copyright © 2020 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity			ASTM D3835
392°F (200°C), 1340 sec <sup>-1</sup>	172 Pa·s	172 Pa·s	
392°F (200°C), 11200 sec <sup>-1</sup>	36.0 Pa·s	36.0 Pa·s	

### Processing Information

Extrusion	Typical Value (English)	Typical Value (SI)
Melt Temperature	360 to 400 °F	182 to 204 °C
Die Temperature	340 to 390 °F	171 to 199 °C

#### Extrusion Notes

Color concentrates with polypropylene (PP), ethylene vinyl acetate (EVA), or low density polyethylene (PE) carriers are most suitable for coloring Versaflex™ HC MT226. Improved color dispersion can be achieved by using higher melt flow concentrates (with a melt flow from 25 - 40g/10 min). Typical loadings for color concentrates are 1% to 5% by weight. Liquid color can be used, but mineral oil based carriers may have a significant effect on the final hardness value. Concentrates based on PVC should not be used. A high color match consistency can be obtained by using precolored compounds available from GLS. The final determination of color concentrate suitability should be determined by customer trials.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Drying is not Required

Rear: 330F-370F  
Center: 350F-400F  
Front: 360F-420F  
Screw: 100-500RPM

#### Notes

<sup>1</sup> Please contact PolyOne GLS Thermoplastic Elastomers for a complete copy of the GLS Healthcare Policy.

1. The Customer must notify GLS of any FDA Class I and/or European Union Class I medical devices for each specific product and application.

2. The Customer shall not knowingly manufacture, use, sell or otherwise supply, directly or indirectly products or compounds made from GLS products in any of the following without prior written approval by GLS for each specific product or application:

- Cosmetics
- Drugs and other Pharmaceuticals
- Temporary or permanent implantation in the human body, regardless of the intended duration of implantation
- Class II and Class III Medical Devices as defined in 21 CFR 860.3 ("Medical Devices")
- Class IIa, IIb and III as defined in Directive 93/42/EEC

<sup>2</sup> Typical values are not to be construed as specifications.

<sup>3</sup> Die C

<sup>4</sup> 2 hr

### CONTACT INFORMATION

#### North America

Avon Lake, United States  
33587 Walker Road  
Avon Lake, OH, United States ,  
44012  
+1 440 930 1000  
+1 844 4AVIENT

#### South America

Sao Paulo, Brazil  
Av. Francisco Nakasato, 1700  
13295-000 Itupeva  
Sao Paulo, Brazil  
+55 11 4593 9200

#### Asia

Shanghai, China  
2F, Block C  
200 Jinsu Road  
Pudong, 201206  
Shanghai, China  
+86 (0) 21 6028 4888

#### Europe

Pommerloch, Luxembourg  
19 Route de Bastogne  
Pommerloch, Luxembourg , L-9638  
+352 269 050 35



avient.com

Copyright ©, 2020 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.