

Versaflex™ VDT 5120-40N

Thermoplastic Elastomer

Key Characteristics

Product Description

Versaflex™ VDT 5120-40N is a vibration and impact damping TPE formulated to bond to a variety of standard and modified nylon materials, including those which are glass-filled, heat stabilized and/or impact modified

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Adhesion • Vibration Damping		
Uses	• Appliance Components • Automotive Applications • Consumer Applications	• Flexible Grips • General Purpose • Overmolding	• Power/Other Tools • Soft Touch Applications • Sporting Goods
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.09	1.09	ASTM D792
Molding Shrinkage - Flow	0.031 to 0.039 in/in	3.1 to 3.9 %	ASTM D955
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress ^{2,3} (100% Strain, 73°F (23°C))	180 psi	1.24 MPa	ASTM D412
Tensile Stress ^{2,3} (300% Strain, 73°F (23°C))	360 psi	2.48 MPa	ASTM D412
Tensile Strength ^{2,3} (Break, 73°F (23°C))	590 psi	4.07 MPa	ASTM D412
Tensile Elongation ^{2,3} (Break, 73°F (23°C))	750 %	750 %	ASTM D412
Tear Strength ² (73°F (23°C))	131 lbf/in	22.9 kN/m	ASTM D624
Compression Set (73°F (23°C))	20 %	20 %	ASTM D395B
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 10 sec)	42	42	ASTM D2240
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity			ASTM D3835
392°F (200°C), 1340 sec ⁻¹	134 Pa·s	134 Pa·s	
392°F (200°C), 11200 sec ⁻¹	25.0 Pa·s	25.0 Pa·s	

Copyright © 2020 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Suggested Max Regrind	20 %	20 %
Rear Temperature	360 to 400 °F	182 to 204 °C
Middle Temperature	470 to 510 °F	243 to 266 °C
Front Temperature	480 to 520 °F	249 to 271 °C
Nozzle Temperature	490 to 530 °F	254 to 277 °C
Mold Temperature	55 to 85 °F	13 to 29 °C
Back Pressure	0.00 to 80.0 psi	0.00 to 0.552 MPa

Injection Notes

Color concentrates based on Versaflex™ VDT 5120-40N are most suitable for coloring Versaflex™ VDT 5120-40N. Typical loadings for color concentrates are 1% to 4% by weight. Concentrates based on PVC should not be used. A high color match consistency can be obtained by using precolored compounds available from GLS. The final determination of color concentrate suitability should be determined by customer trials.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels up to 20% can be used with Versaflex™ VDT 5120-40N with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Versaflex™ VDT 5120-40N has excellent melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 8 - 10 minutes or longer.

Drying is not required

Injection Speed: 3 to 5 in/sec

1st Stage - Boost Pressure: 300 to 8000 psi

2nd Stage - Hold Pressure: 0% of Boost

Hold Time (Thick Part): 0 to 4 sec

Hold Time (Thin Part): 0 to 2 sec

Notes

¹ Typical values are not to be construed as specifications.

² Die C

³ 2 hr

CONTACT INFORMATION

North America

Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States ,
44012
+1 440 930 1000
+1 844 4AVIENT

South America

Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia

Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe

Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35



avient.com

Copyright ©, 2020 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.