

# Versalloy™ HC 9210-55N

## Thermoplastic Elastomer

### Key Characteristics

#### Product Description

Versalloy™ HC 9210-55N is a TPV alloy targeted for injection molding healthcare applications such as disposable medical items, syringe stoppers, and soft-touch overmolding onto surgical grips. Product exhibits exceptional flow properties and surface aesthetics.

- \* Excellent Flow for Long, Thin Flow Paths
- \* Exceptional Colorability
- \* Overmold Adhesion to Polypropylene
- \* Superior Surface Aesthetics
- \* USP Class VI (please see Notes)

#### General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Latin America • North America	
Features	• Good Colorability • Good Processability • Good Surface Finish	• Halogen Free • High Flow • Non-Phthalate Plasticizer	• Recyclable Material
Uses	• Flexible Grips • Medical/Healthcare Applications	• Overmolding • Soft Touch Applications	• Thin-walled Parts
Agency Ratings	• USP Class VI <sup>1</sup>		
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

### Technical Properties <sup>2</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	0.890	0.890	ASTM D792
Molding Shrinkage - Flow	0.016 to 0.022 in/in	1.6 to 2.2 %	ASTM D955
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress <sup>3, 4</sup> (100% Strain, 70°F (21°C))	208 psi	1.44 MPa	ASTM D412
Tensile Stress <sup>3, 4</sup> (300% Strain, 73°F (23°C))	335 psi	2.31 MPa	ASTM D412
Tensile Strength <sup>3, 4</sup> (Break, 73°F (23°C))	580 psi	4.00 MPa	ASTM D412
Tensile Elongation <sup>3, 4</sup> (Break, 73°F (23°C))	610 %	610 %	ASTM D412
Tear Strength <sup>3, 4</sup> (70°F (21°C))	120 lbf/in	21.0 kN/m	ASTM D624
Compression Set			ASTM D395B
73°F (23°C), 22 hr	20 %	20 %	
158°F (70°C), 22 hr	38 %	38 %	
212°F (100°C), 22 hr	44 %	44 %	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 10 sec)	53	53	ASTM D2240

Copyright © 2020 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity 392°F (200°C), 11200 sec <sup>-1</sup>	6.20 Pa·s	6.20 Pa·s	ASTM D3835

**Additional Information**

Versalloy™ HC 9210-55N can be recycled as a filler or impact modifier for polyolefins, or can be recycled by grinding and reintroduction to the molding process. Similar to PP or PE recycling process, if separated appropriately, it can be recycled many times.

Municipality waste stream recycle code is "7" which is designated for "Other".

Please contact GLS Thermoplastic Elastomers for a copy of our Recyclability Compliance letter.

**Processing Information**

Injection	Typical Value (English)	Typical Value (SI)
Suggested Max Re grind	20 %	20 %
Rear Temperature	300 to 370 °F	149 to 188 °C
Middle Temperature	320 to 390 °F	160 to 199 °C
Front Temperature	340 to 410 °F	171 to 210 °C
Nozzle Temperature	340 to 410 °F	171 to 210 °C
Mold Temperature	60 to 80 °F	16 to 27 °C
Back Pressure	100 to 200 psi	0.689 to 1.38 MPa
Screw Speed	50 to 100 rpm	50 to 100 rpm

**Injection Notes**

Color concentrates with polypropylene (PP) carrier are most suitable for coloring Versalloy™ HC 9210-55N. Improved color dispersion can be achieved by using higher melt flow concentrates (with a melt flow from 25 - 40 g/10 min). Typical loadings for color concentrates are 1% to 5% by weight. Concentrates based on PVC should not be used. A high color match consistency can be obtained by the use of precolored compounds available from GLS. The final determination of color concentrate suitability should be determined by customer trials.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels up to 20% can be used with Versalloy™ HC 9210-55N with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Versalloy™ HC 9210-55N has good melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 8 - 10 minutes or longer.

Drying is not Required

Injection Speed: 1 to 5 in/sec  
 1st Stage - Boost Pressure: 300 to 700 psi  
 2nd Stage - Hold Pressure: 70% of Boost  
 Hold Time (Thick Part): 4 to 10 sec  
 Hold Time (Thin Part): 1 to 3 sec

Copyright © 2020 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

**Notes**

<sup>1</sup> Based on the USP Class VI testing conducted on representative grades (HC 9210-45N and HC 9210-70N), this grade should meet USP Class VI requirements for plastics.

Please contact PolyOne GLS Thermoplastic Elastomers for a complete copy of the GLS Healthcare Policy.

1. The Customer must notify GLS of any FDA Class I and/or European Union Class I medical devices for each specific product and application.

2. The Customer shall not knowingly manufacture, use, sell or otherwise supply, directly or indirectly products or compounds made from GLS products in any of the following without prior written approval by GLS for each specific product or application:

a. Cosmetics

b. Drugs and other Pharmaceuticals

c. Temporary or permanent implantation in the human body, regardless of the intended duration of implantation

d. Class II and Class III Medical Devices as defined in 21 CFR 860.3 ("Medical Devices")

e. Class IIa, IIb and III as defined in Directive 93/42/EEC

<sup>2</sup> Typical values are not to be construed as specifications.

<sup>3</sup> Die C

<sup>4</sup> 2 hr

**CONTACT INFORMATION****North America**

Avon Lake, United States  
33587 Walker Road  
Avon Lake, OH, United States ,  
44012  
+1 440 930 1000  
+1 844 4AVIENT

**South America**

Sao Paulo, Brazil  
Av. Francisco Nakasato, 1700  
13295-000 Itupeva  
Sao Paulo, Brazil  
+55 11 4593 9200

**Asia**

Shanghai, China  
2F, Block C  
200 Jinsu Road  
Pudong, 201206  
Shanghai, China  
+86 (0) 21 6028 4888

**Europe**

Pommerloch, Luxembourg  
19 Route de Bastogne  
Pommerloch, Luxembourg , L-9638  
+352 269 050 35



avient.com