

Versollan™ OM 1262NX-9

Thermoplastic Elastomer

Key Characteristics

Product Description

Versollan™ OM 1262NX-9 is a performance TPU alloy designed for thin-wall overmolding onto polycarbonate (PC), ABS, PC/ABS and copolyester substrates.

- Excellent Grip with Matte, Rubbery Finish
- Proven Track Record
- Superior Adhesion to PC, ABS, PC/ABS, PC/PBT and Copolyester

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Moldability	• Good Processability	• Low Gloss
Uses	• Business Equipment • Consumer Applications • Electrical/Electronic Applications	• Flexible Grips • Overmolding • Power/Other Tools	• Thin-walled Parts
Agency Ratings	• UL 94		
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.17	1.17	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
190°C/2.16 kg	7.0 g/10 min	7.0 g/10 min	
200°C/5.0 kg	100 g/10 min	100 g/10 min	
Molding Shrinkage - Flow	9.0E-3 to 0.015 in/in	0.90 to 1.5 %	ASTM D955
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress ^{2,3} (100% Strain, 73°F (23°C))	370 psi	2.55 MPa	ASTM D412
Tensile Stress ^{2,3} (300% Strain, 73°F (23°C))	485 psi	3.34 MPa	ASTM D412
Tensile Strength ^{2,3} (Break, 73°F (23°C))	1110 psi	7.64 MPa	ASTM D412
Tensile Elongation ^{2,3} (Break, 73°F (23°C))	710 %	710 %	ASTM D412
Tear Strength	230 lbf/in	40.3 kN/m	ASTM D624
Compression Set (73°F (23°C), 22 hr)	35 %	35 %	ASTM D395B
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 10 sec)	65	65	ASTM D2240
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.5 mm))	HB	HB	UL 94
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity			ASTM D3835
392°F (200°C), 11200 sec ⁻¹	19.9 Pa·s	19.9 Pa·s	

Copyright © 2020 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	125 to 130 °F	52 to 54 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	< 0.030 %	< 0.030 %
Suggested Max Regrind	20 %	20 %
Rear Temperature	325 to 365 °F	163 to 185 °C
Middle Temperature	335 to 385 °F	168 to 196 °C
Front Temperature	350 to 410 °F	177 to 210 °C
Nozzle Temperature	350 to 410 °F	177 to 210 °C
Mold Temperature	70 to 120 °F	21 to 49 °C
Back Pressure	25.0 to 50.0 psi	0.172 to 0.345 MPa
Screw Speed	25 to 75 rpm	25 to 75 rpm

Injection Notes

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels up to 20% can be used with Versollan™ OM 1262NX-9 with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Versollan™ OM 1262NX-9 should not be left in the barrel for extended idle periods (greater than 5 minutes).

Suggested Dewpoint: -40°F

Injection Speed: 1 to 5 in/sec

1st Stage - Boost Pressure: 200 to 800 psi

2nd Stage - Hold Pressure: 70% of Boost

Hold Time (Thick Part): 4 to 10 sec

Hold Time (Thin Part): 1 to 3 sec

Notes

¹ Typical values are not to be construed as specifications.

² Die C

³ 2 hr

CONTACT INFORMATION

North America

Avon Lake, United States
33587 Walker Road
Avon Lake, OH, United States ,
44012
+1 440 930 1000
+1 844 4AVIENT

South America

Sao Paulo, Brazil
Av. Francisco Nakasato, 1700
13295-000 Itupeva
Sao Paulo, Brazil
+55 11 4593 9200

Asia

Shanghai, China
2F, Block C
200 Jinsu Road
Pudong, 201206
Shanghai, China
+86 (0) 21 6028 4888

Europe

Pommerloch, Luxembourg
19 Route de Bastogne
Pommerloch, Luxembourg , L-9638
+352 269 050 35



avient.com

Copyright ©, 2020 Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. Avient MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.